



Cold Crushing Strength MPa Min.	40	40	40	35	40	35	40	35	40	35
Refractoriness under Load □ Min.	1600	1600	1600	1600	1600	1600	1600	1600	1600	1600
	Semi-Rebonded MgO-Cr <sub>2</sub> O <sub>3</sub> brick				Rebonded MgO-Cr <sub>2</sub> O <sub>3</sub> brick					
Brand	SR-16A	SR-16B	SR-20A	SR-20B	R-16A	R-16B	R-20A	R-20B	R-24	R-26
MgO % Min.	60	60	55	55	65	60	60	60	52	50
Cr <sub>2</sub> O <sub>3</sub> % Min.	16	16	20	20	16	16	20	20	22	24
SiO <sub>2</sub> % Max.	1.5	1.8	1.5	1.8	1.2	1.6	1.2	1.2	1.2	1.2
Apparent Porosity % Max.	17	17	17	17	16	16	16	16	16	16
Cold Crushing Strength MPa Min.	40	35	40	35	45	40	45	40	45	45
Refractoriness under Load □ Min.	1750	1700	1750	1700	1750	1700	1750	1700	1750	1750